


	Specification of Magnetic Powder Core	Mirrack www.mirrack.com(CN) www.mirrack.com.cn(EN)
---	--	--

Part Number	Product Series	Permeability (u)	A _L (nH/N ²)	Coating Color	Coating Material	Coating Breakdown Voltage
MKU467-075	MKU	75	169±8%	Brown	Epoxy	1.5KVac / 0.5mA / 3sec
Description	Toroidal MKU Core					

Core Dimensions

Dimensions	Before Coating		After Coating		Min / Max
	inch	mm	inch	mm	
OD	1.840	46.70	1.875	47.63	Max
ID	0.950	24.10	0.918	23.32	Min
HT	0.710	18.00	0.745	18.92	Max



Physical Characteristics & Packaging

Path Length Le (cm)	Cross Section Ae (cm ²)	Core Volume Ve (cm ³)	Window Area Wa (cm ²)	Weight (g)	Box QTY (pcs)
10.740	1.990	21.300	4.270	142.5±5%	125

Electrical Features (@25°C±2°C)

Test Item	Condition	Value (Typical)
Inductance	Ø1.0 mm, 50TS, 100KHz, 1.0V, 0A	422.5uH±8%
DC-Bias	Ø1.0 mm, 50TS, 100KHz, 1.0V, I _{DC(100 Oe)} = 17.18 A	48% Min
Core Loss	Ø1.0mm, 50TS, 50KHz, 1000Gauss	270mW/cm ³ Max
Hi-Pot	1.5KVac, 0.5mA, 3 sec	PASS

DC Bias Curves

